



HIGH PERFORMANCE VpCI™ COATINGS

VpCI-371



PRODUCT DESCRIPTION

VpCI-371 is a high temperature aluminum solvent-borne silicone coating that provides excellent corrosion resistance on metal substrates. VpCI-371 will dry tack free at room temperature in about 20 minutes to 5B hardness. After the coating has been heated it will have a 9H hardness.

FEATURES

- Heat stability to 1200°F (648.89°C)
- 600 hour salt spray resistance
- 9H pencil hardness
- 200 double rub MEK resistance with no effect
- Brilliant aluminum appearance
- No hard settling of aluminum
- Heat resistance from 400-1200°F (204-649°C) for a prolonged period
- Low VOC

TYPICAL APPLICATIONS

- Automotive industry
- Power generation
- Aviation
- Off shore drilling, etc

VpCI-371 should be thoroughly mixed prior to use. Apply by spray or dip.

TYPICAL PROPERTIES

Appearance	Aluminum liquid
Dry time (tack-free)	20 min. at 0.5-1.0 mil (25 to 50 microns)
Pencil hardness	5B - Ambient Cure 9H - Cured @ 500°F (260°C)
MEK Resistance	200 Double Rubs - After heating
Density	8.4-8.8 lb/gal (1.01-1.06 kg/l)
Solids Wt.	58-62% at 230°F (110°C)
Solids Volume	54-56% at 230°F (110°C)
Viscosity	250 to 1000 cps at 6 RPM
VOC	2.571 lbs/gal (0.31 kg/l)

TESTS

Passes:

ASTM D-2485-91: Standard Test Methods for evaluating coatings for High Temperature Service (Method A and B)

PACKAGING

VpCI-371 is available in 5 gallon (19 liter) metal pails, and 55 gallon (208 liter) metal drums. Keep this package from freezing.

FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:

4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.cortecvci.com>

printed on recycled paper  10% post consumer

Revised 8/11/06. (c) Cortec Corporation 2006. All rights reserved. Supersedes: None.
VpCI™ is a trademark of Cortec Corporation.
© 2006, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited.